

FIBERFLEX PLUS

Compound
SBS
Cold Flexibility
-15°C
CHARACTERISTICS

FIBERFLEX PLUS is a waterproofing membrane made of distilled bitumen modified with SBS (styrene-butadiene-styrene) polymers that make it very elastic, resistant to thermal ageing and flexible at low temperatures.

The elastomeric compound ensures ease of application, reduced consumption of gas and has excellent adhesion properties that ensure, when properly installed, superior bonding and tightness of all joints and overlaps.

CARRIER

The carrier is a composite polyester stabilised with longitudinal glass yarns that combine superior dimensional stability with good mechanical properties.

**INTENDED USE
ACCORDING
"CE" MARK
STANDARDS**

Underlay or intermediate layer in multi-layer systems for roof waterproofing (EN 13707)

FIBERFLEX PLUS
3,0 mm

**AVAILABLE
SURFACE
FINISHES**

Upper surface Polypropylene glossy film; upon request sand, TEX (non-woven black polypropylene "ready-to-paint" film) or plastic HDPE film.

Lower surface Polypropylene or polyethylene fast burning film. For cold applications by means of adhesive the use of sand finishing on the lower surface is recommended.

**USE &
APPLICATION**

FIBERFLEX PLUS is recommended as a base sheet or as an intermediate layer in multi-layer waterproofing constructions for flat, pitched or vaulted roofs, made of reinforced concrete cast on site or prefab, of terraces, under-floorings etc. In case of direct exposure to weathering agents, FIBERFLEX PLUS shall be protected with reflective paint or by a layer of self-protected (mineralised) membrane.

Subject to the type of substrate it shall be installed by means of a propane gas torch, approved adhesives or by mechanical fixing. In any case it is recommended to prepare substrate with fixative bituminous PRIMER W (water base) or PRIMER S (solvent base).

For cold applications on primed concrete surfaces apply with COPERGLUE BASE bituminous adhesive (over horizontal areas) or COPERGLUE VERTICAL (parapets and elevations). Side laps, head joints and small repairs shall be made with COPERGLUE JOINT. For cold applications over insulation board (Polystyrene, PUR or PIR) apply with COPERMAST bituminous mastic.

For correct installation refer to information provided by Copernit Technical Department.

Properties	Test Method	Unit	FIBERFLEX PLUS	Tol.
Length	EN 1848-1	m	10 (-1%)	≥
Width	EN 1848-1	m	1,0 (-1%)	≥
Thickness	EN 1849-1	mm	3,0	±5%
Tensile strength (at break) L/T	EN 12311-1	N/5 cm	500/400	±20%
Elongation (at break) L/T	EN 12311-1	%	35/35	±15
Tear resistance (nail test) L/T	EN 12310-1	N	140/140	±30%
Resistance to static loading	EN 12730 (A)	kg	15	≥
Impact resistance	EN 12691	mm	800	≥
Dimensional stability	EN 1107-1	%	±0,3	≤
Flexibility at low temperature	EN 1109	°C	-15	≤
Flow resistance at elevated temperature	EN 1110	°C	100	≥
Watertightness (method A)	EN 1928	kPa	60	≥
Resistance to water vapor diffusion (μ)	EN 1931	--	20.000	--
Reaction to fire	EN 13501-1	Class	E	--
Resistance to external fire	EN 13501-5	Class	F _{ROOF}	--